



ARL-TN-0737 • FEB 2016



Theoretical Prediction of the Heats of Formation, Densities, and Relative Sensitivities for 3,7-diamino-2,4,6,8-tetranitro-1,5-diazanaphthalene (DATNP) and 3,7-diamino-2,4,6,8-tetranitro-1,5-diazanaphthalene 1,5-N-oxide (DATNPO)

by Edward FC Byrd

NOTICES

Disclaimers

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of manufacturer's or trade names does not constitute an official endorsement or approval of the use thereof.

Destroy this report when it is no longer needed. Do not return it to the originator.



Theoretical Prediction of the Heats of Formation, Densities, and Relative Sensitivities for 3,7-diamino-2,4,6,8-tetranitro-1,5-diazanaphthalene (DATNP) and 3,7-diamino-2,4,6,8-tetranitro-1,5-diazanaphthalene 1,5-N-oxide (DATNPO)

by Edward FC Byrd

Weapons and Materials Research Directorate, ARL

REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing the burden, to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.

PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.

1. REPORT DATE (DD-MM-YYYY) February 2016		2. REPORT TYPE Technical Note		3. DATES COVERED (From - To) 1–30 September 2015	
4. TITLE AND SUBTITLE Theoretical Prediction of the Heats of Formation, Densities, and Relative Sensitivities for 3,7-diamino-2,4,6,8-tetranitro-1,5-diazanaphthalene (DATNP) and 3,7-diamino-2,4,6,8-tetranitro-1,5-diazanaphthalene 1,5-N-oxide (DATNPO)				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S) Edward FC Byrd				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) US Army Research Laboratory ATTN: RDRL-WML-B Aberdeen Proving Ground, MD 21005-5069				8. PERFORMING ORGANIZATION REPORT NUMBER ARL-TN-0737	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10. SPONSOR/MONITOR'S ACRONYM(S)	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution is unlimited.					
13. SUPPLEMENTARY NOTES					
14. ABSTRACT The US Army Research Laboratory–developed series of scripts, written to dramatically simplify the computation of crystalline density and heat of formation, were used to evaluate the performance properties for the 3,7-diamino-2,4,6,8-tetranitro-1,5-diazanaphthalene (DATNP) (1) and 3,7-diamino-2,4,6,8-tetranitro-1,5-diazanaphthalene 1,5-N-oxide (DATNPO) (2) notional energetic materials. Additionally, a qualitative estimation of the impact sensitivities has been calculated. This report outlines the procedures used to generate this information, as well as Cheetah calculations using the predicted crystalline density and heat of formation.					
15. SUBJECT TERMS computational toolbox, script, crystalline density, heat of formation, impact sensitivity, energetic materials					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT	18. NUMBER OF PAGES	19a. NAME OF RESPONSIBLE PERSON
a. REPORT	b. ABSTRACT	c. THIS PAGE			Edward FC Byrd
Unclassified	Unclassified	Unclassified	UU	16	19b. TELEPHONE NUMBER (Include area code) 410-306-0729

Contents

List of Figures	iv
List of Tables	iv
Acknowledgments	v
1. Introduction	1
2. Results and Discussion	1
3. Conclusions	4
4. References	5
List of Symbols, Abbreviations, and Acronyms	6
Distribution List	7

List of Figures

Fig. 1	Optimized structure of a) 1 and b) 2	2
Fig. 2	Electrostatic potential map of 1 , without a) and with b) molecule overlay.....	3
Fig. 3	Electrostatic potential map of 2 , without a) and with b) molecule overlay.....	3

List of Tables

Table 1	Computed heats of formation and crystalline densities for 1 and 2	2
Table 2	Cheetah predicted properties for 1 and 2	3

Acknowledgments

Dr Betsy Rice and Jennifer J Hare are acknowledged for their efforts in the original coding of the neutral heat of formation and EDAT tools, respectively. Dr Anthony Yau is acknowledged for his work in revising the EDAT code. Dr James Ianni (Applications Engineer with Lockheed-Martin, contractor to the US Army Research Laboratory Department of Defense [DOD] Supercomputing Resource Center [ARL DSRC]) is acknowledged for his “gsubmit” script, initially written for the ARL DSRC. Dr Betsy Rice is acknowledged for running the Cheetah calculations. All computations were performed at the ARL DSRC, Aberdeen Proving Ground, MD. Calculations were performed at the behest of Dr Gary K Windler (Los Alamos National Laboratory).

INTENTIONALLY LEFT BLANK.

1. Introduction

US Army Research Laboratory (ARL) researchers have achieved robust theoretical models capable of predicting performance properties, such as heats of formation,^{1,2} densities,^{3,4} and impact sensitivity⁵ of energetic materials, and have begun growing advanced synthesis capabilities to realize notional materials. This dual capability allows synthetic and formulation chemists to safely and quickly screen candidate materials to focus efforts only on the most promising compounds. For an in-depth explanation of the different theoretical methods employed herein, please refer to previous works.^{6,7} This technical note will detail theoretical predictions of heat of formation, density, sensitivity, and performance for the 3,7-diamino-2,4,6,8-tetranitro-1,5-diazanaphthalene (DATNP) (**1**) and 3,7-diamino-2,4,6,8-tetranitro-1,5-diazanaphthalene 1,5-N-oxide (DATNPO) (**2**).⁸

2. Results and Discussion

The properties of **1** and **2** (Figs. 1a–b) were predicted using the ARL-developed scripts described in more detail in a previous report.⁷ For the estimation of the impact sensitivities, the electrostatic maps on the 0.001 isosurfaces were generated with the scalar range of the electrostatic surface potential (ESP) ranging from –0.05 to 0.075. Recall that for this visualization methodology, regions of large positive charge (i.e., electron deficient regions, labeled as red) over the backbone of the structure tend to indicate increased sensitivity.




Fig. 1 Optimized structure of a) 1 and b) 2

The computed heats of formation and crystalline densities for these molecules are presented in Table 1.

Table 1 Computed heats of formation and crystalline densities for 1 and 2

Molecule	Solid phase heat of formation (kcal/mol)	Density (g/cm ³)
1	25.899	1.863
2	46.903	1.932

Additionally, we plot the ESP maps for **1** (Figs. 2a–b) and **2** (Figs. 3a–b) with and without the molecule overlaid on the ESP. When the images are analyzed, we would quantify both molecules as slightly sensitive to insensitive. We performed Cheetah 8.0 calculations⁹ to predict the performance parameters using the predicted heats of formation and densities. At the Chapman-Jouguet point, Cheetah yields the values shown in Table 2.




Fig. 2 Electrostatic potential map of 1, without a) and with b) molecule overlay




Fig. 3 Electrostatic potential map of 2, without a) and with b) molecule overlay

Table 2 Cheetah predicted properties for 1 and 2

Molecule	Pressure (GPa)	Shock velocity (km/s)	Temperature (K)	Total energy of detonation (TNT eqv. per cm ³)	Total energy of detonation (TNT eqv. per g)
1	27.182	8.033	3204.0	1.175	1.043
2	32.745	8.643	3692.8	1.397	1.196

Note: TNT = trinitrotoluene

3. Conclusions

The ARL-developed software tools were used to predict the heats of formation and crystalline densities of the 3,7-diamino-2,4,6,8-tetranitro-1,5-diazanaphthalene (DATNP) (**1**) and 3,7-diamino-2,4,6,8-tetranitro-1,5-diazanaphthalene 1,5-N-oxide (DATNPO) (**2**) molecules. Using this predicted data, we then ran Cheetah calculations to predict the performance of these materials. Additionally, we predicted the qualitative impact sensitivities of these compounds using electrostatic potential maps. This information has been transitioned back to the requesting synthetic chemist, Dr Gary K Windler of Los Alamos National Laboratory.

4. References

1. Byrd EFC, Rice BM. Improved prediction of heats of formation of energetic materials using quantum mechanical calculations. *J Phys Chem A*. 2006;110(3):1005–1013; *ibid* 2009;113:5813.
2. Byrd EFC, Rice BM. A comparison of methods to predict solid phase heats of formation of molecular energetic salts. *J Phys Chem A*. 2009;113(1):345–352.
3. Rice BM, Hare JJ, Byrd EFC. Accurate predictions of crystal densities using quantum mechanical molecular volumes. *J Phys Chem A*. 2007;111(42):10874–10879.
4. Rice BM, Byrd EFC. Evaluation of electrostatic descriptors for predicting crystalline density. *J Comp Chem*. 2013;34(25):2146–2151.
5. Rice BM, Hare JJ. A quantum mechanical investigation of the relation between impact sensitivity and the charge distribution in energetic molecules. *J Phys Chem A*. 2002;106(9):1770–1783.
6. Byrd EFC. Theoretical prediction of the heat of formation, density and relative sensitivity for 3,7-dinitro-[1,2,4]triazolo[5,1-c][1,2,4]triazin-4-amine. Aberdeen Proving Ground (MD): Army Research Laboratory (US); 2015 Apr. Report No.: ARL-TN-0680.
7. Byrd EFC. On the failure of correlating partitioned electrostatic surface potentials using Bader's atoms-in-molecules theory to impact sensitivities. Aberdeen Proving Ground (MD): Army Research Laboratory (US); 2013 Sep. Report No.: ARL-TR-6206.
8. Windler GK. Los Alamos National Laboratory, Los Alamos, NM. Private communications, 2015 Sep.
9. Bastea S, Fried LE, Glaeseman KR, Howard WM, Kuo IFW, Souers PC, Vitello PA. Cheetah 8.0 thermochemical code. Livermore (CA): Energetic Materials Center, Lawrence Livermore National Laboratory; 2015.

List of Symbols, Abbreviations, and Acronyms

ARL	US Army Research Laboratory
cm ³	grams per cubic centimeter
DATNP	3,7-diamino-2,4,6,8-tetranitro-1,5-diazanaphthalene
DATNPO	3,7-diamino-2,4,6,8-tetranitro-1,5-diazanaphthalene 1,5-N-oxide
DSRC	Department of Defense (DOD) Supercomputing Resource Center
ESP	electrostatic surface potential
kcal/mol	kilocalories per mole (unit of energy)
TNT	trinitrotoluene

1 DEFENSE TECHNICAL
(PDF) INFORMATION CTR
DTIC OCA

2 DIRECTOR
(PDF) US ARMY RESEARCH LAB
RDRL CIO LL
IMAL HRA MAIL & RECORDS
MGMT

1 GOVT PRINTG OFC
(PDF) A MALHOTRA

1 NAVAL RSRCH LAB
(PDF) TECH LIB

2 US ARMY ARDEC
(PDF) A DISTASIO
S NICOLICH

17 DIR USARL
(PDF) RDRL WM
B FORCH
D LYON
RDRL WMM
J ZABINSKI
RDRL WML
M ZOLTOSKI
RDRL WML A
W OBERLE
RDRL WML B
N TRIVEDI
J MORRIS
B RICE
E BYRD
RDRL WML C
S AUBERT
J SABATINI
J BANNING
RDRL WML D
R BEYER
RDRL WML E
P WEINACHT
RDRL WML G
W DRYSDALE
RDRL WML H
R EHLERS
J NEWILL

INTENTIONALLY LEFT BLANK.